

MAXTREAT[®] FIBRENET C

High Performance High Strength, Carbon Fibre System for Structural Strengthening and Retrofitting



Maxtreat[®] Fibrenet C is a carbon fibre composite wrapping system where Maxtreat[®] Fibrenet C is used in conjunction with an epoxy sealer cum primer, Maxtreat[®] Primer and a high build Maxtreat[®] Saturant.

Uses

Maxtreat[®] Fibrenet C is a carbon fibre composite system for strengthening columns, beams and slabs of load bearing structures particularly where improvement to shear strength and deformation characteristics is required. It is ideal for seismic retrofitting also. Typical applications include piers, columns, beams, slabs, retaining walls, masonry bridges, pipes, chimney, tunnels and other structures.

Benefits

- **Very high strength to thickness or weight ratio-** Appreciable increase in strength and load carrying capacity without significant increase in dead load.
- **Enhanced stiffness, shear & tensile capacities-** Increased load carrying capacity and better resistance to seismic forces and deflection.
- **Chemical Resistant-** Excellent resistance to acids and alkalis
- **Flexible-** Can be applied on any shape or contour of substrate
- **Thin Sections-** Can be effectively used in space constrained areas.
- **Creep and Fatigue Resistance-** Ideal for conditions of sustained loading and repeated loading.
- **Economical-** Easy to install, time and labor saving.

Properties

	Maxtreat [®] Fibrenet C200	Maxtreat [®] Fibrenet C400
Fibre Orientation	Unidirectional	Unidirectional
Weight of Fibre	200-230 gm/m ²	400-430 gm/m ²
Density of Fibre	1.80 gm/cc	1.80 gm/cc
Fibre Thickness	0.25 mm	0.38-0.4 mm
Ultimate Elongation	1.7%	1.7%
Tensile Strength	4000 MPa	4000 MPa

Tensile Modulus	240 GPa	240 GPa
------------------------	---------	---------

Maxtreat[®] Primer

Maxtreat[®] Primer is a two component solvent free epoxy primer for use as a primer/sealer coat for Maxtreat[®] Fibrenet System.

Properties

Mix Density	1.11±0.03 gm/cc
Volume of Solids	88-92%
Pot Life at 30°C	~25 minutes
Touch Dry Time at 30°C	8-12 hours
Adhesion Bond Strength to Concrete	>4 N/mm ²
Full Cure	7 days

Maxtreat[®] Saturant

Maxtreat[®] Saturant is a two component solvent free epoxy saturant/adhesive for use in conjunction with Maxtreat[®] Fibrenet System.

Properties

Mix Density	1.40±0.05 gm/cc
Volume of Solids	100%
Pot Life at 30°C	60-90 minutes
Open Time at 30°C	90-120 minutes
Adhesion Bond Strength to Concrete	>4 N/mm ²
Compressive Strength at 7 days	>50 N/mm ²

Instructions for Use

Surface Preparation

Concrete surfaces to be treated shall be free from oil residues, demoulding agents, curing compounds, grout holes and protrusions. In case of distressed structures, the concrete surface to be wrapped shall be structurally repaired prior to treatment. Structural damages shall be repaired by using epoxy grouting/appropriate mortar from the Thermax range.

All depressions, imperfections etc., shall be repaired by using Maxtreat[®] EPG epoxy putty.

Mixing

Before mixing, the contents of each can should be thoroughly stirred to disperse any settlement, which may have taken place during storage. The base and hardener are emptied into a suitable container and the material is thoroughly mixed for at least 3 minutes. Mechanical mixing using a heavy-duty slow speed (300 - 500 rpm), flameproof drill, fitted with a mixing paddle is recommended.

Primer

The mixed material of Maxtreat® Primer is applied over the prepared and cleaned surface. The application shall be carried out using a brush and allowed to dry for about 24 hours before application of saturant. The wet film thickness shall be maintained @ 100-150 microns.

Saturant

The mixed material of Maxtreat® Saturant is applied over the tack free primer. The wet thickness shall be maintained at 150-225 microns.

Maxtreat® Fibrenet C

The Maxtreat fabric shall be cut to required size and then pressed first by gloved hand on to the saturant applied area and then with a stiff spatula or a surface roller to remove air bubbles. One more coat of Maxtreat® Saturant is applied over the carbon fabric after a minimum lapse of 30 minutes.

The same procedure shall be followed for multiple layer fibre strengthening.

Note: Care shall be taken to ensure that the fibre orientation is not disturbed while applying the second coat of saturant.

Curing

The coatings will become tack free in approximately 4-6 hours and be fully cured in 7 days.

Cleaning

Tools and equipment should be cleaned with solvent immediately after use. Hands and skin shall be washed with soap, or an industrial hand cleaner.

Limitations

Maxtreat® Fibrenet C reinforced system is only recommended for use as described in the uses section of this datasheet. The performance of Maxtreat® Fibrenet C system is limited to the specifications and recommendations as described in this datasheet.

For increased fire rating Maxtreat® Fibrenet C system can be overlaid with a 1:3 Cement sand / Plaster Gypsum of suitable thickness.

Health & Safety Instructions

Some people are sensitive to epoxy resin systems and may develop dermatitis on skin contact. Rubber gloves and/or barrier creams, protective clothing, goggles and respirator shall be worn on handling the materials. Sufficient mechanical and/or local exhaust ventilation shall be provided to maintain easy working conditions. If contact with skin or eyes occurs, washing with plenty of water is suggested. Solvent should not be used. If irritation persists, immediate medical advice shall be sought. Smoking is prohibited during application/handling of the product.

Storage

Shelf Life

All the above products have a shelf life of 12 months if stored in unopened containers below 35°C. Maxtreat® Fibrenet C can be used even up to 3 years.

Packing

Maxtreat® Fibrenet C is supplied as below:

GSM	Width, mm	Length, m	Area, m ²
C200	500	50	25
C400	500	50	25

Packing

Maxtreat® Primer: 2.7 and 4 ltr.

Maxtreat® Saturant: 2.7 and 4 ltr.

Maxtreat® EPG: 0.5 & 1 ltr.

MAXTREAT[®] FIBRENET C

Coverage


Product	WFT (microns)	DFT (microns)	Coverage per coat/ltr
Maxtreat [®] Primer	100-150	100-150	7.0-10.0 m ²
Maxtreat [®] Saturant	150-225	150-225	3.5-5 m ²

Other Segments:

- Concrete Admixtures • Surface Treatments • Grouts & Anchors • Repair & Rehabilitation
- Protective Coatings • Industrial Flooring • Waterproofing • Sealants • Adhesives

Disclaimer: The information contained in this document is true and accurate to the best of our knowledge and is based on our experience & test results. It is always the Company's endeavor to give true and accurate information however as it does not have any direct and/or continuing control on the use of the Products, the Company cannot accept any liability, direct or indirect as a consequence of the use of Products. In the event of any doubt upon any critical parameter it is advisable to seek clarification from our technical representative.

We reserve the right to amend any product details without notice. Copyright © Thermax Limited Edition: (TCC/TDS/0223RN)



THERMAX

Thermax Limited
Environment House, Plot No.90-92
BG Block, MIDC, Bhosari,
Pune 411 026, India.
Tel: +91-20-67156000
Fax: +91-20-27120206
Customer Care: 18002090115 (India
toll free)
Email : enquiry@thermaxglobal.com

Ahmedabad

Tel: +91-79-26575408 • Fax: +91-79-65577270

Bengaluru

Tel: +91-80-22371721 • Fax: +91-80-22371726

Chennai

Tel: +91-44-24303400 • Fax: +91-44-24353841

Delhi

Tel: +91-11- 46087200 • Fax: +91-11- 26145311

Hyderabad

Tel: +91-40-23253700 • Fax: +91-40-23253799

Kolkata

Tel: +91-33-66070800 • Fax: +91-33-66070999

Mumbai

Tel: +91-22-67542222 • Fax: +91-22-22040859

Thermax World-wide

UK, USA, UAE, Germany, Belgium, Denmark,
Russia, Saudi Arabia, Thailand, Malaysia,
Bangladesh, Sri Lanka, China, Philippines,
Peru, Chile, Kenya, Nigeria, Brazil, Indonesia

Website: www.thermaxglobal.com

Thermax Business Portfolio

Chemicals

Absorption Cooling

Air Pollution Control

Boilers & Heaters

Power

Water & Waste Solutions

Solar